

**PATENT ABSTRACTS OF JAPAN**

(11)Publication number : 01-271476

(43)Date of publication of application : 30.10.1989

(51)Int.Cl.

C09K 3/10

(21)Application number : 63-099257 (71)Applicant : SANYO CHEM IND LTD

(22)Date of filing : 21.04.1988 (72)Inventor : TANAKA HIROTADA
MURATA TSUTOMU**(54) MOISTURE-CURABLE SEALANT****(57)Abstract:**

PURPOSE: To obtain the title one-pack, substantially unplasticized sealant for construction, excellent in an ability to be pressed out, water resistance, heat resistance, etc., by mixing a reaction product of a specified polyol with specified aromatic and aliphatic polyisocyanates with a specified curing agent and a specified filler.

CONSTITUTION: 100 pts.wt. reaction product of a polyol (A) which is preferably selected from among a polyoxyalkylene polyol, a polymer polyol and a polybutadienepolyol with an aromatic polyisocyanate (B) which is preferably toluene diisocyanate and/or 4,4'-diphenylmethane diisocyanate and an aliphatic type polyisocyanate (C) which is preferably aliphatic and/or alicyclic polyisocyanates [wherein the B/C molar ratio is preferably 10/90-60/40, and the (B+C)/A equivalent ratio is preferably 1.2-3.0] is mixed with preferably, 0.0001-3.0 pts.wt. curing catalyst of, for example, a metallic type and/or an amine type and preferably, 0.5-500 pts.wt. pigment, solvent and filler such as an extender to obtain a sealant having an NCO content of, preferably, 0.2-0.8wt.%.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office